#### DESCRIPTIVE MODEL OF COMSTOCK EPITHERMAL VEINS

By Dan L. Mosier, Donald A. Singer, and Byron R. Berger

APPROXIMATE SYNONYM Epithermal gold (quartz-adularia) alkali-chloride type.

DESCRIPTION Gold, electrum, silver sulfosalts, and argentite in vuggy quartz-adularia veins hosted by felsic to intermediate volcanic rocks that overlie predominantly elastic sedimentary rocks, and their metamorphic equivalents (see fig. 106).

GENERAL REFERENCES Buchanan (1980), Boyle (1979).

#### GEOLOGICAL ENVIRONMENT

Rock Types Host rocks are andesite, dacite, quartz latite, rhyodacite, rhyolite; and associated sedimentary rocks. Mineralization related to talc-alkaline or bimodal volcanism.

Textures Porphyritic.

Age Range Mainly Tertiary (most are 40-3.7 my.).

Depositional Environment Calc-alkaline and bimodal volcanism and associated intrusive activity over basement rocks composed of elastic sedimentary rocks and their metamorphic equivalents. Volcanic-related geothermal systems lack access to saline fluids from basement sources.

<u>Tectonic Setting(s)</u> Through-going fracture systems, major normal faults, fractures related to doming, ring fracture zones, joints.

Associated Deposit Types Placer gold and epithermal quartz-alunite Au.

### DEPOSIT DESCRIPTION

Mineralogy Argentite + gold or electrum ± silver sulfosalts ± naumannite. Galena, sphalerite, chalcopyrite, tellurides, hematite, and arsenopyrite are moderate to sparse. Gangue minerals are quartz + pyrite ± adularia ± calcite ± sericite ± chlorite. Barite, fluorite, rhodochrosite, kaolinite, and montmorillonite are moderate to sparse. Ore minerals constitute only a few percent of vein.

Texture/Structure Banded veins, open space filling, lamellar quartz, stockwork.

Alteration From top to bottom of system: quartz + kaolinite + montmorillonite ± zeolite ± barite ± calcite; quartz + illite; quartz + adularia ± illite; quartz + chlorite; presence of adularia is variable.

 $\underline{\text{Ore Controls}}$  Through-going anastomosing fracture systems, centers of intrusive activity. Hanging wall more favorable.

<u>Weathering</u> Bleached country rock, limonite, jarosite, goethite, alunite, hematite, argillization with kaolinite.

## EXAMPLES

Comstock, USNV Guanajuato, MXCO (Becker, 1882) (Buchanan, 1980; Wandke and Martinez, 1928)

# GRADE AND TONNAGE MODEL OF COMSTOCK EPITHERMAL VEINS

By Dan L. Mosier, Donald A. Singer, and Byron R. Berger

COMMENTS See figs. 113-116.

## DEPOSITS

Name	Country	<u>Name</u>		Country
Aurora Bodie Bovard Calico Calistoga Comstock Divide Dolores El Rincon Fairview Fuke Gold Mountain Guanacevi Guanajuato Hostotipaquilla Katherine Kushikino-Arakawa Mochikoshi Mogollon Nawaji Oatman	USNV USCA USCA USCA USCA USCA USCA USCA USCA		Ohguchi Ohito Olinghouse Orient Patterson Republic Rosario Sand Springs Searchlight Seikoshi Seven Trough Sheep Tank Silver City Taio Tayoltita Toi Tonopah Tuscarora Weaver Yugashima	JAPN JAPN JAPN USNV USWA USCA USWA HNDR USNV USNV JAPN USNV JAPN USNV USAZ USNV JAPN MXCO JAPN USNV USAZ USNV USAZ USNV




Figure 113. Tonnages of Comstock epithermal vein deposits.






Figure 114. Gold grades of Comstock epithermal vein deposits.



SILVER GRADE IN GRAMS PER TONNE

Figure 115. Silver grades of Comstock epithermal vein deposits.



LEAD GRADE IN PERCENT

0.1

0.0 0.01

C.

**Figure 116.** By-product grades of Comstock epithermal vein deposits.  $\underline{A}$ , Copper.  $\underline{B}$ , Zinc.  $\underline{C}$ , Lead.